



TECHNICAL BULLETIN

Raybo Chemical Company

TELEPHONE: 304-525-5171

RAYBO 85 Rustib Resists Corrosion Undercutting

REFERENCE	FEATURES	SYSTEM	COMMENTS	USAGE (%)	REFERENCE
	Resists Corrosion Undercutting of Paint	Solvent	Cationic	0.5% of Solids	

PERFORMANCE RAYBO 85 is a cationic wetting agent. Because of its polarity, it is attracted to the metal surface forming a mono-molecular hydrophobic layer. This affinity increases adhesion and resistance to corrosion undercutting in coatings containing RAYBO 85.

When added to coatings pigmented with transition metals containing pigments like phthalocyanine blue, insure that the surfactant demand has been met. If it has not, RAYBO 85 will be absorbed onto the pigment, reducing corrosion protection.

ADVANTAGES

- Polar bonding with metal surface for increased corrosion resistance.
- Listed with USDA

RECOMMENDATIONS For corrosion Resistance – 0.5% of Total Solids
Post addition recommended

PHYSICAL DATA**

Weight/Gallon7.45 lbs
 Consistency.....Paste
 Melting Point.....70 - 80° F

CONTAINER SIZES North America: 5 gal. pail*, 55 gal. drum, and bulk.
 Global Zones: 5 gal. pail*, 55 gal. drum.

20100104

* One gallon containers available upon request.

** Typical Properties; not sales specifications.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty either expressed or implied, is made or intended. Use by customer should be based upon its own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

